

Technical Data Sheet

Hifax TKC 805P E C12886

Polypropylene Compounds

Product Description

Hifax TKC 805P E C12886 is a 33% talc filled PP TPO copolymer, with good flowability, UV resistance, high stiffness and very good impact/stiffness balance. Formula is improved to offer better aspect, especially on tiger stripes. The product is available in different color matched, pellet form. This grade is delivered in C12886 black color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Exterior Automotive Applications; Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Flow; High Stiffness; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	11	g/10 min	ISO 1133-1
Density, (23 °C)	1.15	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2600	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	25	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	35	kJ/m ²	ISO 179-1/1eA
(-30 °C)	3	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	138	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	60	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.