

Technical Data Sheet

**Hifax TRC 228P 2 C4 C15250**



Polypropylene Compounds

**Product Description**

*“Hifax TRC 228P 2 C4” is a 12% talc filled PP copolymer, with good processability, high impact resistance, good scratch resistance, very good surface appearance and good UV resistance. This grade is available in custom color, pellet form.*

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Weather Resistance; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	0.98	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1650	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	22	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	30	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	4.8	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	101	°C	ISO 75B-1, -2