

## Technical Data Sheet

**Hifax TRC 432X BLACK**

Polypropylene Compounds

**Product Description**

Hifax TRC 432X BLACK is a 20% talc filled PP copolymer, with high flowability and good impact/stiffness balance. The product is available in black color, pellet form.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Exterior Trim
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	High Flow

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2400	MPa	ISO 178/A1
Flexural Strength, (23 °C, Tech. A)	32	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	21	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	12	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	3.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Vicat Softening Temperature, (B50)	60	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	55	°C	ISO 75A-1, -2