

## Technical Data Sheet

### Hifax TYC 1168P 598F ANTHRACITE



Polypropylene Compounds

#### Product Description

Hifax TYC 1168P 598F ANTHRACITE very high melt flow for easy and fast molding and has low density, which reduces part weight. It has good stiffness and excellent cold temperature impact. It is typically used for mold-in color exterior trim and fascia applications.

<b>Application</b>	Automotive Parts; Bumpers; Exterior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Dimensional Stability; Good Flow; Good Impact Resistance; Good Moldability; High Stiffness; Low Shrinkage; Low Temperature Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	35	g/10 min	ASTM D1238
Density, (23 °C, Method A)	0.98	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	1600	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	18	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	>500	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	54	kJ/m <sup>2</sup>	ISO 179
(-30 °C)	5.1	kJ/m <sup>2</sup>	ISO 179
Multi-axial Impact Strength, (-30 °C, 2.2 m/s, 3.2 mm plaque) Failure Mode Ductile.	22	J	ASTM D3763
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			