

Technical Data Sheet

**Hifax TYC 1168P 668D MED AND SIL**



Polypropylene Compounds

**Product Description**

Hifax TYC 1168P 668D MED AND SIL very high melt flow for easy and fast molding and has low density, which reduces part weight. It has good stiffness and excellent cold temperature impact. It is typically used for mold-in color exterior trim and fascia applications.

|                          |   |
|--------------------------|---|
| <b>Application</b>       | Automotive Parts; Bumpers; Exterior Automotive Applications   |
| <b>Market</b>            | Automotive  |
| <b>Processing Method</b> | Injection Molding   |
| <b>Attribute</b>         | Good Dimensional Stability; Good Flow; Good Impact Resistance; Good Moldability; High Stiffness; Low Shrinkage; Low Temperature Impact Resistance |

| Typical Properties  | Nominal Value | Units             | Test Method   |
|---|---------------|-------------------|---------------|
| <b>Physical</b>   |               |                   |               |
| Melt Flow Rate, (230 °C/2.16 kg)                              | 35            | g/10 min          | ASTM D1238    |
| Density, (23 °C, Method A)                                    | 0.98          | g/cm <sup>3</sup> | ISO 1183-1    |
| <b>Mechanical</b>   |               |                   |               |
| Flexural Modulus, (23 °C)                                     | 1600          | MPa               | ISO 178       |
| Tensile Stress at Yield, (23 °C)                              | 18            | MPa               | ISO 527-1, -2 |
| <b>Impact</b>   |               |                   |               |
| Charpy Impact Strength - Notched                              |               |                   |               |
| (23 °C)   | 52            | kJ/m <sup>2</sup> | ISO 179       |
| (-30 °C)  | 6.0           | kJ/m <sup>2</sup> | ISO 179       |
| Multi-axial Impact Strength, (-30 °C, 2.2 m/s, 3.2 mm plaque) | 22            | J                 | ASTM D3763    |
| Failure Mode Ductile.   |               |                   |               |
| <b>Additional Information</b>                                 |               |                   |               |
| Mold Shrinkage  |               |                   | ISO 294-4     |
| Please contact LyondellBasell for shrinkage recommendations.  |               |                   |               |