

## Technical Data Sheet

### Hifax TYC 1348P RXF



Polypropylene Compounds

#### Product Description

Hifax TYC 1348P RXF is a high melt flow resin for easy and fast molding that has low density, which reduces part weight and improves paint adhesion. Good stiffness and excellent cold temperature impact. It is typically used for molded-in color (MIC) exterior trim and fascia applications.

<b>Application</b>	Automotive Parts; Bumpers; Exterior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Dimensional Stability; Good Flow; Good Impact Resistance; Good Moldability; High Stiffness; Low Shrinkage; Low Temperature Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ASTM D1238
Density, (23 °C, Method A)	0.985	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	1600	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	18	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C)	50	kJ/m <sup>2</sup>	ISO 179
Multi-axial Impact Strength, (-30 °C, 2.2 m/s, 3.2 mm plaque) Failure Mode Ductile.	22	J	ASTM D3763
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			