

## Technical Data Sheet

### Hifax TYC 356P G14008



Polypropylene Compounds

#### Product Description

Hifax TYC 356P G14008 is a talc filled PP copolymer, with high stiffness, good impact resistance and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G14008 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Bumpers
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Impact Resistance; Good UV Resistance; High Stiffness

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	35	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2050	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	49	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	6	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	57	°C	ISO 75A-1, -2