



Hifax TYC 773P

Compounded Polyolefin

Product Description

Hifax TYC 773P very high melt flow, 1,350 MPa flexural modulus, UV-stabilized, mineral-filled, paintable, thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It was designed primarily for use in thin-walled bumper fascia applications.

Product Characteristics

| | |
|--------------------------------------|--|
| Test Method used | ISO |
| Processing Methods | Injection Molding |
| Features | Good Dimensional Stability, High Flow , Good Impact Resistance , Good Moldability , Paintable, High Stiffness, Good Toughness, Good Weather Resistance |
| Typical Customer Applications | Bumpers |

| Typical Properties | Method | Value | Unit |
|---|---------------------|---------|-------------------|
| Physical | | | |
| Melt Flow Rate (230°C/2.16kg) | ASTM D 1238 | 22 | g/10 min |
| Density (Method A) | ISO 1183 | 0.97 | g/cm ³ |
| Mechanical | | | |
| Tensile Stress at Yield (23 °C) | ISO 527-1, -2 | 17 | MPa |
| Tensile Strain at Break (23 °C) | ISO 527-1, -2 | 500 | % |
| Tensile Strain at Yield (23 °C) | ISO 527-1, -2 | 7 | % |
| Flexural modulus (23 °C) | ISO 178 | 1350 | MPa |
| Impact | | | |
| Notched izod impact strength | ISO 180 | | |
| (-40 °C) | | 6.0 | kJ/m ² |
| (23 °C) | | 50 | kJ/m ² |
| Hardness | | | |
| Shore hardness D | ISO 868/ASTM D 2240 | 60 | |
| Thermal | | | |
| CLTE, Flow (-22 to 212°F (-30 to 100°C)) | ASTM D 696 | 5.3e-05 | cm/cm/°C |
| Heat deflection temperature B (0.45 MPa) Unannealed | ISO 75B-1, -2 | 100 | °C |
| Additional Information | | | |
| Mold shrinkage | ISO 294-4 | | |