



Hostacom 65F4-2

Compounded Polyolefin

Product Description

Hostacom 65F4-2 conventional melt flow, 1,900 MPa flexural modulus, 20% talc-filled polypropylene homopolymer is designed for balanced stiffness, impact resistance, dimensional stability, colorability and heat aging performance.

Product Characteristics

Test Method used	ASTM
Processing Methods	Injection Molding
Features	Good Colorability, Good Dimensional Stability, Good Heat Aging Resistance, High Heat Resistance, Homopolymer, Good Impact Resistance, Good Stiffness
Typical Customer Applications	Appliances, Automotive Parts, Hair Dryers, Shavers and Steam Irons, Housewares

Typical Properties	Method	Value	Unit
Physical			
Density -Specific Gravity	ASTM D 792	1.05	g/cm ³
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	4	g/10 min
Mechanical			
Flexural Modulus	ASTM D 790	1900	MPa
Tensile Strength @ Yield	ASTM D 638	31	MPa
Tensile Strength @ Break	ASTM D 638	29	MPa
Tensile Elongation @ Yield	ASTM D 638	4	%
Tensile Elongation @ Brk	ASTM D 638	70	%
Impact			
Notched Izod Impact (23 °C)	ASTM D 256	37	J/m
Hardness			
Rockwell Hardness (R-Scale)	ASTM D 785	84	
Thermal			
DTUL @66psi - Unannealed	ASTM D 648	109	°C
Additional Information			
Mold shrink, Linear-Flow	ASTM D 955	1.2	%