

## Technical Data Sheet

### Hostacom BFT 30



Polypropylene Compounds

#### Product Description

Hostacom BFT 30 is a 30% talc filled PP copolymer, with good stiffness. The product is available in black color, pellet form.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Automotive Parts
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	6	g/10 min	ISO 1133-1
Density, (23 °C)	1.15	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2400	MPa	ISO 178/A1
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	6	kJ/m <sup>2</sup>	ISO 180/1A