

Technical Data Sheet

Hostacom CR 250 F G71260



Polypropylene Compounds

Product Description

Hostacom CR 250 F is a 15% talc filled elastomer modified PP, with medium melt flow rate, excellent impact/stiffness balance and very good processability.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Automotive Parts; Instrument Panels; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Ductile; Good Abrasion Resistance; Good Color Stability; Good Processability; Good Stiffness; Good Surface Finish; High Impact Resistance; Low to No Odor; Medium Flow; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	9.5	g/10 min	ISO 1133-1
Density, (23 °C)	1.02	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched			
(23 °C)	30	kJ/m ²	ISO 179-1/1eA
(0 °C)	7	kJ/m ²	ISO 179-1/1eA