

## Technical Data Sheet

**Hostacom CR 250 F M G31463**

Polypropylene Compounds

**Product Description**

Hostacom CR 250 F M G31463 is a 16% talc filled PP copolymer, with high flowability, excellent impact/stiffness balance, good scratch resistance and good UV resistance. Product is available as a customized color matched, pellet form. It has been designed using the latest advancements in resin synthesis and compounding technology. This grade is delivered in G13463 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Status</b>	Commercial: Active
<b>Availability</b>	Europe
<b>Application</b>	Instrument Panels
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good UV Resistance; High Flow; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	12	g/10 min	ISO 1133-1
Density, (23 °C)	1.03	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1650	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	18	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	35	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-40 °C)	2.5	kJ/m <sup>2</sup>	ISO 179-1/1eA
Notched Izod Impact Strength			
(23 °C)	30	kJ/m <sup>2</sup>	ISO 180/1A
(-40 °C)	3	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	95	°C	ISO 75B-1, -2

**Notes**

These are typical property values not to be construed as specification limits.