

Technical Data Sheet

Hostacom CR 250 F/M T2 C16006



Polypropylene Compounds

Product Description

Hostacom CR 250 F/M T2 C16006 is a talc filled impact modified polypropylene, with good impact/stiffness balance, good scratch resistance, and UV resistance.

Product is available as a customized color matched, pellet form. This grade is delivered in C16006 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; High Flow; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	21	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	1.03	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1850	MPa	ISO 178
Tensile Stress at Yield	21	MPa	ISO 527-1, -2
Tensile Strain at Break	70	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	21	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	100	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	54	°C	ISO 75A-1, -2