

## Technical Data Sheet

### *Hostacom* DYS 707N T 2082 (DN71)



Polypropylene Compounds

#### Product Description

*Hostacom* DYS 707N T 2082 is an unfilled impact modified polypropylene, with good processability and excellent impact/stiffness balance.

Product is available as a customized color matched, pellet form. This grade is delivered in 2082 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	High Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.91	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	1150	MPa	ISO 178
Tensile Stress at Yield	18	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	45	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-40 °C)	4.5	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	76	°C	ISO 75B-1, -2