

Technical Data Sheet

*Hostacom* EKC 671N 2083 (DN72)



Polypropylene Compounds

**Product Description**

*Hostacom* EKC 671N 2083 (DN72) is a 20% talc filled PP copolymer, with good flowability and high stiffness. Product is available as a customized color matched, pellet form. This grade is delivered in 2083 (DN72) color version.

<b>Status</b>	Commercial: Active
<b>Availability</b>	Asia-Pacific
<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Flow; Good Stiffness; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus	2650	MPa	ISO 178
Tensile Stress at Yield	24	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	6	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	118	°C	ISO 75B-1, -2