

## Technical Data Sheet

### *Hostacom* EP3307 T 2065 (EBONY)



Polypropylene Compounds

#### Product Description

*Hostacom* EP3307 T 2065 is an unfilled polypropylene copolymer, with high impact resistance and good UV resistance.

Product is available as a customized color matched, pellet form. This grade is delivered in 2065 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	1100	MPa	ISO 178
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
Tensile Strain at Break	350	%	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	45	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	6	kJ/m <sup>2</sup>	ISO 180/1A