

Technical Data Sheet

Hostacom ERC 161N C12616

Polypropylene Compounds

Product Description

Hostacom ERC 161N is a 16% talc filled PP copolymer, with excellent flowability, good stiffness and good scratch resistance. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	High Flow; High Stiffness; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	1.01	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2200	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	27	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	5	kJ/m ²	ISO 179-1/1eA
(-30 °C)	2,2	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	64	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.