

## Technical Data Sheet

### *Hostacom* ERC 213N NATURAL



Polypropylene Compounds

#### Product Description

*Hostacom* ERC 213N is a 15% talc filled PP copolymer, with good flow ability, excellent impact/stiffness balance and high scratch resistance. Product is available as a customized color matched, pellet form.

This grade is not intended for medical and pharmaceutical applications.

<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.01	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	1850	MPa	ISO 178
Tensile Strength, (23 °C)	21	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	35	kJ/m <sup>2</sup>	ISO 180/1A