

Technical Data Sheet

Hostacom EYC 772N NATRL



Polypropylene Compounds

Product Description

Hostacom EYC 772N NATRL very high melt flow, mineral-filled polypropylene copolymer has a good balance of properties and processability. It is typically used for automotive interior applications that require high rigidity and good scratch and mar resistance.

Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	35	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	2600	MPa	ISO 178
Tensile Stress at Yield	25	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	7	kJ/m ²	ISO 180
(-30 °C)	2.5	kJ/m ²	ISO 180
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	112	°C	ISO 75B-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			