

Technical Data Sheet

Hostacom GP621-2 C BLACK



Polypropylene Compounds

Product Description

Hostacom GP621-2 medium melt flow, 3,000 MPa flexural modulus, 20% talc-filled polypropylene homopolymer is designed for high stiffness and good colorability.

Status	Commercial: Active
Availability	Asia-Pacific
Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Colorability; Good Processability; High Rigidity

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	3000	MPa	ISO 178
Tensile Stress at Yield	34	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	2.5	kJ/m ²	ISO 180/1A