

Technical Data Sheet

Hostacom HKG 607N C16002



Polypropylene Compounds

Product Description

Hostacom HKG 607N C16002 is a 30% glass fiber reinforced polypropylene, with medium flow and high stiffness. Product is available as a customized color matched, pellet form. This grade is delivered in C16002 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts
Market	Automotive
Processing Method	Injection Molding
Attribute	High Stiffness; Medium Flow; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	9	g/10 min	ISO 1133-1
Density, (23 °C)	1.13	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	6600	MPa	ISO 178
Tensile Stress at Yield	86	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	7.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	153	°C	ISO 75B-1, -2