

## Technical Data Sheet

**Hostacom M4 W01 100000**

Polypropylene Compounds

**Product Description**

Hostacom M4 W01 100000 is a 40% talc filled PP homopolymer, with high melt flow rate. Product is available as a customized color matched, pellet form. This grade is delivered in Black color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Underhood
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	28	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	28	cm <sup>3</sup> /10 min	ISO 1133-1
Density, (23 °C)	1.21	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Tensile Modulus, (23 °C)	3700	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	30	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C)	2.5	kJ/m <sup>2</sup>	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	20	kJ/m <sup>2</sup>	ISO 179-1/1eU
<b>Thermal</b>			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	85	°C	ISO 75A-1, -2