

## Technical Data Sheet

### *Hostacom* PF062-2C NA BLK P23943



Polypropylene Compounds

#### Product Description

*Hostacom* PF062-2C NA BLK P23943 high melt flow, 4,500 MPa flexural modulus, precolored, chemically coupled, 20% glass fiber-reinforced polypropylene homopolymer has good impact strength, high stiffness and very good moldfilling capability.

<b>Application</b>	Automotive Parts; Exterior Automotive Applications; Underhood
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density	1.04	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	4500	MPa	ISO 178
Tensile Stress at Yield	80	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	7.0	kJ/m <sup>2</sup>	ISO 180
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.