

## Technical Data Sheet

### Hostacom PPH MT20 FC BLK 73500



Polypropylene Compounds

#### Product Description

Hostacom PPH MT20 FC BLK 73500 is a 20% mineral filled PP homopolymer with medium melt flow rate.

Product is not yet UL certified.

*This grade is not intended for medical, pharmaceutical, and drinking water applications.*

<b>Application</b>	White Goods
<b>Market</b>	Electrical / Electronics
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	9	cm <sup>3</sup> /10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Tensile Modulus, (23 °C)	2600	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	33	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Unnotched, (23 °C)	46	kJ/m <sup>2</sup>	ISO 179-1/1eU
<b>Thermal</b>			
Vicat Softening Temperature, (A50)	152	°C	ISO 306