

Technical Data Sheet

**Hostacom TRC 104N C12990**



Polypropylene Compounds

**Product Description**

Hostacom TRC 104N C12990 is a 20% talc filled PP copolymer, with good processability and high impact/stiffness balance. Product is available as a customized color matched, pellet form. This grade is delivered in C12990 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Instrument Panels; Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Excellent Processability; Good Impact Resistance; Good Stiffness; High Flow; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	30	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	106	°C	ISO 75B-1, -2