

## Technical Data Sheet

### Hostacom TRC 1193N 110E BLACK



Polypropylene Compounds

#### Product Description

Hostacom TRC 1193N 110E BLACK is high melt flow, 1,900 MPa flexural modulus, low density thermoplastic polyolefin (TPO) resin. It has an excellent balance of processability, rigidity, impact, scratch and mar resistance. It is typically used for injection molding of Instrumental Panels and other interior trim parts or components with good surface appearance properties.

<b>Application</b>	Instrument Panels; Interior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Excellent Processability; Good Moldability; High Flow; High Impact Resistance; High Rigidity; Low Density; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	0.99	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	1900	MPa	ISO 178
Tensile Stress at Yield	19	MPa	ISO 527-1, -2
Tensile Strain at Yield	6	%	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	45	kJ/m <sup>2</sup>	ISO 180
(-30 °C)	8	kJ/m <sup>2</sup>	ISO 180
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	107	°C	ISO 75B-1, -2
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.