

## Technical Data Sheet

### Hostacom TRC 1193N E5 D72A38



Polypropylene Compounds

#### Product Description

Hostacom TRC 1193N E5 D72A38 is high melt flow, low density mineral filled polypropylene copolymer for injection moulding.

It has an excellent balance of processability, rigidity, impact, scratch and mar resistance.

The grade has been specifically designed for moulding of interior trim parts or components that require good dimensional stability and superior surface appearance properties.

This grade is delivered in cool light grey color version which refers to Tesla NEU\_138i.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Interior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	High Impact Resistance; High Stiffness

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density, (23 °C)	1.01	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	19	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Notch A)	55	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-40 °C)	3.6	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Heat Deflection Temperature A, (1.80 MPa, Unannealed)	53	°C	ISO 75A-1, -2