

## Technical Data Sheet

### Hostacom TRC 152N G72366



Polypropylene Compounds

#### Product Description

Hostacom TRC 152N G72366 is a 20% talc filled PP copolymer, with low gloss, good surface appearance and outstanding scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G72366 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Automotive Parts; Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Processability; High Impact Resistance; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	19	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	18	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	23	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	45	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-30 °C)	5	kJ/m <sup>2</sup>	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	No Break		ISO 179-1/1eU
<b>Thermal</b>			
Vicat Softening Temperature, (A50)	125	°C	ISO 306