

Technical Data Sheet

*Hostacom* TRC 160N HF LS NATURAL



Polypropylene Compounds

**Product Description**

*Hostacom* TRC 160N HF LS NATURAL is a 16% mineral filled, polypropylene copolymer for injection molding. It combines excellent stiffness/impact balance, good scratch resistance, low odor and excellent flowability properties with good dimensional stability. It is typically used for molding of automotive interior trim parts.

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Automotive Parts; Interior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Moldability; Good Stiffness; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	32	g/10 min	ISO 1133-1
Density, (23 °C)	1.00	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	1750	MPa	ISO 178
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C)	50	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	98	°C	ISO 75B-1, -2
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.

**Notes**

These are typical property values not to be construed as specification limits.