

## Technical Data Sheet

**Hostacom TRC 352N E1 G62514**

Polypropylene Compounds

**Product Description**

Hostacom TRC 352N E1 is a 20% talc filled PP copolymer, with excellent blooming resistance at elevated temperatures, very good impact/stiffness balance, very good processability, very good scratch resistance and very good surface appearance. Please contact LyondellBasell for shrinkage recommendations. This grade is delivered in Color G62514.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Status</b>	Commercial: Active
<b>Availability</b>	Europe
<b>Application</b>	Automotive Parts; Instrument Panels; Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Moldability; High Impact Resistance; Non Blooming; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1900	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	21.5	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	30	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-30 °C)	3	kJ/m <sup>2</sup>	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	No Break		ISO 179-1/1eU
<b>Thermal</b>			
Vicat Softening Temperature, (A50)	136	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	54	°C	ISO 75A-1, -2

**Notes**

These are typical property values not to be construed as specification limits.