

Technical Data Sheet

Hostacom TRC 452N NAT



Polypropylene Compounds

Product Description

Hostacom TRC 452N is a 20% talc filled PP copolymer, with excellent impact/stiffness balance and good flowability and good scratch resistance, outstanding blooming resistance at elevated temperatures and good antistatic behavior. Product is available as a customized color matched, pellet form. Please contact Basell for shrinkage recommendations. This grade is delivered in natural color.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts; Instrument Panels; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Moldability; High Impact Resistance; Non Blooming; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1900	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	22	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	25	kJ/m ²	ISO 179-1/1eA
(-30 °C)	3	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	54	°C	ISO 75A-1, -2