

## Technical Data Sheet

### Hostacom TRC 787N D E G91428



Polypropylene Compounds

#### Product Description

Hostacom TRC 787N D E is a 20% talc filled PP copolymer, with excellent impact/stiffness balance, good processability, high scratch resistance and good surface appearance. This grade is delivered in customer customized colors. The product is available in G91428 color version, pellet form.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Status</b>	Commercial: Active
<b>Availability</b>	Europe
<b>Application</b>	Automotive Parts; Interior Automotive Applications; Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Antistatic; Ductile; Good Abrasion Resistance; Good Color Stability; Good Processability; Good Stiffness; Good Surface Finish; High Flow; High Impact Resistance; Low Density; Low Temperature Impact Resistance; Low to No Odor; Low VOC Emission; Pleasing Surface Appearance; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	21	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	18	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	48	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	6,6	kJ/m <sup>2</sup>	ISO 180/1A