

## Technical Data Sheet

### Hostacom TRC 787N NATRL



Polypropylene Compounds

#### Product Description

Hostacom TRC 787N NATRL high melt flow, 1,850 MPa flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of processability, rigidity, and impact and scratch and mar resistance. It is typically used for molded-in color automotive instrument panels.

<b>Application</b>	Instrument Panels; Interior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Colorability; Good Flow; Good Moldability; High Impact Resistance; High Stiffness; Low Gloss; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	21	g/10 min	ASTM D1238
Density, (23 °C)	1.04	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	1850	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	19	MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C)	7	%	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	48	kJ/m <sup>2</sup>	ISO 180
(-30 °C)	6.6	kJ/m <sup>2</sup>	ISO 180
<b>Thermal</b>			
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	103	°C	ISO 75B-1, -2
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			