

Technical Data Sheet

Hostacom TYS 696N 2067



Polypropylene Compounds

Product Description

Hostacom TYS 696N 2067 is an unfilled impact modified polypropylene, with high melt flow rate and high impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 2067 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	High Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	30	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	1050	MPa	ISO 178
Tensile Stress at Yield	19.5	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	45	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	84	°C	ISO 75B-1, -2