

Technical Data Sheet

Hostacom X M2 T11 2082 (DN71)



Polypropylene Compounds

Product Description

Hostacom X M2 T11 2082 is a 20% talc filled impact modified polypropylene, with medium flow and high impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 2082 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	High Impact Resistance; Medium Flow; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	6.5	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	1.05	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	2200	MPa	ISO 178
Tensile Stress at Yield	22	MPa	ISO 527-1, -2
Tensile Strain at Break	150	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	30	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	110	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	58	°C	ISO 75A-1, -2