

## Technical Data Sheet

### Hostacom X M2 U38 C12306



Polypropylene Compounds

#### Product Description

Hostacom X M2 U38 C12306 is a 22% talc filled PP copolymer, with high melt flow rate and excellent stiffness. Product is available as a customized color matched, pellet form. This grade is delivered in C12306 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Interior Trims
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Stiffness

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2200	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	23	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength (23 °C)	5	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	2.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	104	°C	ISO 75B-1, -2