

Technical Data Sheet

Hostacom XBR 169G C5 C15974



Polypropylene Compounds

Product Description

Hostacom XBR 169 G C5 is a 15% talc filled PP copolymer, with good processability, excellent impact resistance, excellent stiffness and excellent scratch resistance. Product is available as a customized color matched, pellet form.

Application	Automotive Parts; Interior Trims
Market	Automotive
Attribute	Good Moldability

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	14	g/10 min	ISO 1133-1
Density, (23 °C)	1.00	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1760	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	25	kJ/m ²	ISO 179-1/1eA