



## Hostalen PP H2222 36

### Polypropylene, Impact Copolymer

#### Product Description

**Hostalen PP H2222 36** is a polypropylene blockcopolymer grey coloured similar to RAL 7032 (pebble grey).

The product has a high heat stability and extremely high extraction stability. .

For regulatory information please refer to *Hostalen* PP H2222 36 Product Stewardship Bulletin (PSB).

Hostalen PP H2222 36 is not intended for medical and pharmaceutical applications.

#### Product Characteristics

<b>Status</b>	Commercial: Active
<b>Test Method used</b>	ISO
<b>Availability</b>	Europe
<b>Processing Methods</b>	Extrusion Pipe Sheet and Semi Finished Products
<b>Features</b>	Antioxidant, Block Copolymer
<b>Typical Customer Applications</b>	Industrial, Plumbing, Heating & Cooling

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	0.912	g/cm <sup>3</sup>
Melt flow rate (MFR)	ISO 1133		
(230°C/2.16Kg)		0.3	g/10 min
(190°C/5.0kg)		0.5	g/10 min
(230°C/5.0kg)		1.3	g/10 min
<b>Mechanical</b>			
Tensile Modulus (23 °C, v = 1 mm/min, Secant)	ISO 527-1, -2	1350	MPa
Tensile Stress at Yield (23 °C, v = 50 mm/min)	ISO 527-1, -2	30	MPa
Tensile Strain at Yield (23 °C, v = 50 mm/min)	ISO 527-1, -2	12	%
Tensile Creep Modulus 1h	ISO 899-1	1050	MPa
Tensile Creep Modulus 1000h	ISO 899-1	510	MPa
<b>Impact</b>			
Charpy notched impact strength	ISO 179		
(23 °C)		50	kJ/m <sup>2</sup>
(0 °C)		13	kJ/m <sup>2</sup>
(-30 °C)		5.8	kJ/m <sup>2</sup>
<b>Hardness</b>			
Shore hardness (Shore D (3 sec))	ISO 868	67	
<b>Thermal</b>			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	91	°C
Vicat softening temperature	ISO 306		
(VST/A/50 K/h (10 N))		158	°C
(VST/B/50 K/h (50 N))		81	°C
Melting Temperature	ISO 3146	165	°C

## Additional Properties

---

### Processing:

The recommended conditions will depend on the type of equipment used and the size and wall thickness of the pipe or profile required.

Recommended melt temperatures: 200-230 °C

Recommended injection moulding temperatures: 200-280 °C

### Notes

Typical properties; not to be construed as specifications.