

Technical Data Sheet

Indure X76 K9WA LC Black



Polypropylene Compounds

Product Description

Indure X76 K9WA LC Black engineered polyolefin material is typically used for various automotive exterior-trim applications. It offers an excellent combination of scratch resistance, UV resistance, high-gloss part appearance, good processability and a balance of stiffness and impact resistance.

Application	Automotive Parts; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	32	g/10 min	ISO 1133-1
Density	0.91	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C, 2 mm/min)	950	MPa	ISO 178
Tensile Stress at Yield, (23 °C, 50 mm/min)	20	MPa	ISO 527-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			