

Technical Data Sheet

Matrixx 12N5006

Polypropylene
LyondellBasell Industries
Engineering Plastics

General	
Material Status	• Commercial: Active
Availability	• North America
Additive	• Flame Retardant
Features	• Flame Retardant • Low Blooming
Appearance	• Colors Available
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.940	0.938 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	2600 psi	17.9 MPa	ASTM D638
Flexural Modulus - Tangent	125000 psi	862 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	No Break	No Break	ASTM D256
Gardner Impact	190 in·lb	21.5 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	175 °F	79.4 °C	ASTM D648
RTI Str	239 °F	115 °C	UL 746B

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-2	V-2	UL 94

Notes

These are typical property values not to be construed as specification limits.