

Technical Data Sheet

Matrixx 14A4150

Polypropylene
LyondellBasell Industries
Engineering Plastics

General	
Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Talc, 15% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.31	1.31 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	4000 psi	27.6 MPa	ASTM D638
Flexural Modulus	450000 psi	3100 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.50 ft·lb/in	27 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	240 °F	116 °C	
264 Psi (1.8 Mpa), Unannealed	155 °F	68.3 °C	
RTI Elec	149 °F	65.0 °C	UL 746B
RTI Imp	149 °F	65.0 °C	UL 746B
RTI Str	149 °F	65.0 °C	UL 746B

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-0	V-0	UL 94

Additional Information
The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with Matrixx test methods.

Notes

These are typical property values not to be construed as specification limits.