

Technical Data Sheet

# Matrixx 14N6020

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

General	
Material Status	• Commercial: Active
Availability	• North America
Additive	• Flame Retardant
Features	• Flame Retardant • Low Blooming
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.990	0.988 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	18 g/10 min	18 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	5000 psi	34.5 MPa	ASTM D638
Flexural Modulus	210000 psi	1450 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.50 ft·lb/in	27 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	205 °F	96.1 °C	ASTM D648
RTI Elec	149 °F	65.0 °C	UL 746B
RTI Imp	149 °F	65.0 °C	UL 746B
RTI Str	149 °F	65.0 °C	UL 746B

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-0	V-0	UL 94

**Additional Information**  
The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with Matrixx test methods.

**Notes**

These are typical property values not to be construed as specification limits.