

Technical Data Sheet

Matrixx CP0401VA12561

Polypropylene
 LyondellBasell Industries
 Engineering Plastics

Product Description
 CP0401VA12561 is an Unfilled, Hi-Impact, Co-Polymer, Polypropylene

General			
Material Status	• Commercial: Active		
Availability	• North America		
Features	• Copolymer	• High Impact Resistance	
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.902	0.900 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	1.1 g/10 min	1.1 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	3050 psi	21.0 MPa	ASTM D638
Tensile Elongation (Break)	470 %	470 %	ASTM D638
Flexural Modulus	117000 psi	807 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	No Break	No Break	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	55	55	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	153 °F	67.0 °C	ASTM D648

Technical Data Sheet

Matrixx CP0401VA12561

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	370 to 450 °F	188 to 232 °C
Middle Temperature	370 to 450 °F	188 to 232 °C
Front Temperature	370 to 450 °F	188 to 232 °C
Processing (Melt) Temp	390 to 450 °F	199 to 232 °C
Mold Temperature	70 to 120 °F	21 to 49 °C
Injection Rate	Moderate	Moderate
Back Pressure	20.0 to 300 psi	0.138 to 2.07 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Notes

These are typical property values not to be construed as specification limits.