

## Technical Data Sheet

**Moplen EP310M HP**

Polypropylene, Impact Copolymer

**Product Description**

*Moplen EP310M HP* is a heterophasic copolymer, used in film applications for lamination on other substrates where high impact at room and low temperatures is needed. Moreover EP310M HP features a good stiffness. This new grade is produced using a non-phthalate catalyst system favored by customers in applications intended for food contact. The film viscosity achieved with *Moplen EP310M HP* offers good processability on cast lines. This polypropylene heterophasic copolymer exhibits high impact, good puncture, good tear resistance, high seal strength and seal integrity.

<b>Status</b>	Commercial: Active
<b>Availability</b>	Africa-Middle East; Europe
<b>Application</b>	Bags & Pouches; Food Packaging Film; Impact Modification; Lamination Film; Surface Protection Film
<b>Market</b>	Flexible Packaging
<b>Processing Method</b>	Cast Film
<b>Attribute</b>	Good Processability; Impact Copolymer; Medium Flow

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	7.5	g/10 min	ISO 1133-1
Density	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Tensile Modulus	1050	MPa	ISO 527-1, -2
Tensile Stress at Yield	21	MPa	ISO 527-1, -2
Tensile Strain at Break		%	ISO 527-1, -2
Tensile Strain at Yield	6	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	45	kJ/m <sup>2</sup>	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	9	kJ/m <sup>2</sup>	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	7	kJ/m <sup>2</sup>	ISO 179
Ductile/Brittle Transition Temperature	-55	°C	ISO 6603-2
<b>Hardness</b>			
Ball Indentation Hardness	46	MPa	ISO 2039-1
<b>Thermal</b>			
Vicat Softening Temperature, (A50)	144	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	80	°C	ISO 75B-1, -2

**Notes**

These are typical property values not to be construed as specification limits.