



Moplen HP2814

Polypropylene, Homopolymer

Product Description

Moplen HP2814 is used in extrusion applications. It has a very narrow molecular weight distribution and it is formulated with an anti-gasfading stabilisation package. Moplen HP2814 is used in the production of continuous filaments. Typical applications are high-tenacity yarns (HTY) and spunbond nonwovens. For regulatory information please refer to Moplen HP2814 Product Stewardship Bulletin (PSB).

Product Characteristics

Status	Development
Test Method used	ISO
Availability	Europe, Asia-Pacific, Africa-Middle East
Processing Methods	Continuous Filament/Spinning, Spun Bond
Features	Homopolymer, Narrow Molecular Weight Distribution
Typical Customer Applications	Filament Yarn, Nonwoven Spunbond

Typical Properties	Method	Value	Unit
Physical			
Melt flow rate (MFR) (230°C/2.16kg)	ISO 1133	25	g/10 min
Mechanical			
Tensile Stress at Break	ISO 527-1, -2	20	N/mm ²
Tensile Stress at Yield	ISO 527-1, -2	20	N/mm ²
Tensile Strain at Break	ISO 527-1, -2	>500	%
Tensile Strain at Yield	ISO 527-1, -2	11	%
Flexural modulus	ISO 178	1300	N/mm ²
Impact			
Charpy unnotched impact strength	ISO 179	4	kJ/m ²
		140	kJ/m ²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	90	°C
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	153	°C
		(B50 (50°C/h 50N))	93

Notes

Typical properties; not to be construed as specifications.