



Moplen HP456H

Polypropylene, Homopolymer

Product Description

Moplen HP456H is used in extrusion and thermoforming applications. It is formulated with a low water-carry-over additive package. Typical applications are strapping, monofilaments and tapes. For regulatory information please refer to Moplen HP456H Product Stewardship Bulletin (PSB).

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe, Asia-Pacific, Australia/NZ, Africa-Middle East, Latin America
Processing Methods	Tapes & Raffia
Features	Homopolymer
Typical Customer Applications	Raffia/Tapes/Strapping

Typical Properties	Method	Value	Unit
Physical			
Melt flow rate (MFR) (230°C/2.16kg)	ISO 1133	1.8	g/10 min
Mechanical			
Tensile Stress at Break	ISO 527-1, -2	25	N/mm ²
Tensile Stress at Yield	ISO 527-1, -2	34	N/mm ²
Tensile Strain at Break	ISO 527-1, -2	>500	%
Tensile Strain at Yield	ISO 527-1, -2	11	%
Flexural modulus	ISO 178	1400	N/mm ²
Impact			
Charpy unnotched impact strength	ISO 179	240	kJ/m ²
Charpy notched impact strength	ISO 179	11	kJ/m ²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	90	°C
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	153	°C
(B50 (50°C/h 50N))		93	°C

Notes

Typical properties; not to be construed as specifications.