



## Moplen HP483R

### Polypropylene, Homopolymer

#### Product Description

Moplen HP483R is a homopolymer for injection moulding with antistatic and slip agent addition that exhibits good stiffness combined with a good flowability. The main applications of Moplen HP483R are caps, closures, furniture and TWIM. For regulatory information please refer to Moplen HP483R Product Stewardship Bulletin ( PSB )

#### Product Characteristics

<b>Status</b>	Commercial: Active
<b>Test Method used</b>	ISO
<b>Availability</b>	Europe, Africa-Middle East
<b>Processing Methods</b>	Injection Molding
<b>Features</b>	Antistatic, Good Flow, Homopolymer, Unspecified Slip, Good Stiffness
<b>Typical Customer Applications</b>	Caps & Closures, Furniture, Housewares, Opaque Containers

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	0.9	g/cm <sup>3</sup>
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	27	g/10 min
<b>Mechanical</b>			
Tensile Modulus	ISO 527-1, -2	1400	MPa
Tensile Stress at Yield	ISO 527-1, -2	32	MPa
Tensile Strain at Break	ISO 527-1, -2	>50	%
Tensile Strain at Yield	ISO 527-1, -2	9	%
<b>Impact</b>			
Charpy notched impact strength (23 °C, Type 1, Edgewise, Notch A)	ISO 179	2	kJ/m <sup>2</sup>
<b>Hardness</b>			
Ball indentation hardness (H 358/30)	ISO 2039-1	68	MPa
<b>Thermal</b>			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	80	°C
Vicat softening temperature A/50	ISO 306	151	°C
Vicat softening temperature B/50	ISO 306	85	°C

#### Notes

Typical properties; not to be construed as specifications.