

## Technical Data Sheet

### Moplen HP551R



Polypropylene, Homopolymer

#### Product Description

Moplen HP551R is a homopolymer suitable for extrusion applications. This grade is formulated with anti gas fading stabilisation package. Moplen HP551R is used for production of continuous filaments (CF), Bulk continuous filaments (BCF) and staple fibres.

Typical applications are carpet, upholstery, ropes etc.

<b>Status</b>	Commercial: Active
<b>Availability</b>	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe
<b>Application</b>	Bulk Continuous Filament & Continuous Filament; Filament Yarn
<b>Market</b>	Textile
<b>Processing Method</b>	Continuous Filament/Spinning; Staple Fiber
<b>Attribute</b>	Gas-fading Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	34	cm <sup>3</sup> /10 min	ISO 1133-1
<b>Mechanical</b>			
Flexural Modulus	1350	MPa	ISO 178
Tensile Stress at Yield	32	MPa	ISO 527-1, -2
Tensile Strain at Yield	10	%	ISO 527-1, -2
<b>Thermal</b>			
Vicat Softening Temperature, (A/50 N)	153	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	97	°C	ISO 75B-1, -2

#### Notes

These are typical property values not to be construed as specification limits.