



Moplen RP2795

Polypropylene, Random Copolymer

Product Description

"Moplen" RP2795 is a random copolymer for manufacturing high transparent cast films. The product contains slip- and antiblock agents. It exhibits very good optical properties and good heat weldability. Main applications are packaging of foodstuffs such as sweets, pasta, biscuits and snacks, packaging of books, stationary, blankets, shirts and hosiery.

"Moplen" RP2795 is suitable for food contact.

For regulatory information please refer to "Moplen" RP2795 Product Stewardship Bulletin (PSB).

Product Characteristics

Status	Commercial: Active
Test Method used	ISO ASTM
Availability	Europe, Africa-Middle East
Processing Methods	Cast Film
Features	Unspecified Antiblocking , High Clarity, Controlled Rheology, Random Copolymer, Unspecified Slip
Typical Customer Applications	Cast Film, Food Packaging Film, Stationery Film, Textile Packaging Film

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.900	g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	10.5	g/10 min
Mechanical			
Tensile Modulus (1 mm/min)	ISO 527-1, -2	810	MPa
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	26	MPa
Tensile Strain at Yield (50 mm/min)	ISO 527-1, -2	13	%
Impact			
Charpy notched impact strength	ISO 179		
(23 °C, Type 1, Edgewise, Notch A)		5.1	kJ/m ²
(0 °C, Type 1, Edgewise, Notch A)		2.2	kJ/m ²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	69	°C

Additional Properties

Typical film properties of laboratory casting line:
 Gloss 45°, ASTM D 2457, 50 µm: 88
 Haze, ASTM D 1003, 50 µm: <1.3%
 Tensile Young modulus, ASTM D 882, 25 mm/min, 50 µm: 490 MPa
 Stress at Yield, ASTM D 882, 500 mm/min, 50 µm, 17 MPa
 Elongation at Yield, ASTM D 882, 500 mm/min, 50 µm: 14%
 Stress at break, ASTM D 882, 500 mm/min, 50 µm, 43 MPa
 Elongation at break, ASTM D 882, 500 mm/min, 50 µm: 980%
 Coefficient of friction, ASTM D 1894, Static: 0.2
 Coefficient of friction, ASTM D 1894, Dynamic: 0.15