

Technical Data Sheet

Moplen RP348T HP



Polypropylene, Random Copolymer

Product Description

Moplen RP348T HP is a random copolymer for injection molding with a clarifier and antistatic based additivation, offering a very good flowability and transparency.

Moplen RP348T HP is typically used in thin walled packaging and appreciated by customers for its good aesthetic appearance. It can be processed at significantly low temperature, allowing energy savings and improved productivity due to reduced cycle times.

This grade is not intended for medical and pharmaceutical applications.

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Clear Containers; Housewares; Sports, Leisure & Toys
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Contains Antistat; High Flow; High Transparency; Nucleated

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	48	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1100	MPa	ISO 527-1, -2
Tensile Stress at Yield	29	MPa	ISO 527-1, -2
Tensile Strain at Break	>50	%	ISO 527-1, -2
Tensile Strain at Yield	11	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	4.5	kJ/m ²	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	2.5	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature, (A50)	130	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	70	°C	ISO 75B-1, -2
Optical			
Haze, (1 mm - injection molded disc)	9	%	ASTM D1003

Notes

These are typical property values not to be construed as specification limits.